

PRODUCT DATA SHEET

SikaTop[®]-121

FIBER REINFORCED POLYMER MODIFIED REPAIR MORTAR

DESCRIPTION

SikaTop[®]-121 is a two-component cement based, polymer modified, trowelable adhesive and filling compound for the protection and repair of concrete surfaces.

USES

- Thin layer render
- Levelling of surfaces
- Protective coating for bridges parapets, retaining walls, etc.
- Filling compound to level off irregularities and to fill blowholes and fine honeycombing
- Rendering for reservoirs, ponds. etc

CHARACTERISTICS / ADVANTAGES

- Pre-batched product
- User friendly
- Good mechanical strengths
- Excellent adhesion
- High resistance to chloride salts

PRODUCT INFORMATION

Chemical base	Cement, selected aggregates and additives
Packaging	25 kg set (A+B)
Appearance / Colour	Component A: White liquid Component B: Grey powder
Shelf life	9 months from date of production if stored properly in unopened original packing.
Storage conditions	Store in a dry area in original sealed packaging at temperatures between 5 °C and 30 °C
Density	~2.1 kg/L at +25 °C (fresh density of mortar)

TECHNICAL INFORMATION

Compressive Strength	7 days	~30 N/mm ²	(ASTM C-109)
	28 days	~42 N/mm ²	
Tensile Strength in Flexure	7 days	~7 N/mm ²	(ASTM C-348)
	28 days	~10 N/mm ²	

SYSTEMS

System Structure	Repair Mortar	
	SikaTop®-122	Concrete Repair Mortar
	Pore sealer and levelling mortar	
	SikaTop®-121	Normal Use

APPLICATION INFORMATION

Mixing Ratio	Parts by weight A : B = 1 : 4.5 - 5, depending on required consistency
Consumption	This depends on the substrate roughness and thickness of layer applied. As a guide, ~21 kg of fresh mortar per cm thick per m ²
Yield	25 kg set yields approximately 12.0 litres of mortar
Layer Thickness	Minimum 2 mm/ maximum 5 mm
Ambient Air Temperature	+5 °C minimum; +35 °C maximum
Substrate Temperature	+5 °C minimum; +35 °C maximum
Pot Life	~45 minutes at +30 °C

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete:

The concrete shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. De-laminated, weak, damaged, and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.

MIXING

SikaTop®-121 can be mixed with a low speed (<250 rpm) hand drill mixer. Shake Component A (liquid) and pour it into a suitable mixing vessel. While mixing add Component B (powder) into the mix. Mix the two components together for a minimum 3 minutes. DO NOT ADD WATER.

APPLICATION

SikaTop®-121 can be applied manually using traditional techniques. Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and do not allow to dry. Before application remove excess water e.g. with a clean sponge. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water.

Apply first a scratch coat by firmly scrapping the repair mortar over the substrate surface to form a thin layer and fill any pores or pits in the surface. Ensure the whole surface to be repaired is covered by the scratch coat. Build up layers from bottom to top by pressing mortar well into the repair area. The surface can be finished according to the requirements using a float while wet or with a relevant rough-cast tool as soon as the mortar has started to stiffen.

CURING TREATMENT

Protect the fresh mortar immediately from premature drying using an appropriate curing method e.g. curing compound, moist geotextile membrane, polythene sheet, etc.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

LIMITATIONS

- DO NOT ADD WATER
- Avoid application in direct sun and/ or strong wind and/ or rain.
- Protect freshly applied material from freezing and rain.
- Apply only to sound, prepared substrate.
- Do not add additional water during the surface finishing as this will cause discolouration and cracking.
- Maximum thickness per application : 5 mm
- Variation in cement could cause shade differences in colour of the mortar.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia Head Office and

Jl. Raya Cibinong-Bekasi Km.20
Limusnunggal-Cileungsi
Bogor 16820-Indonesia
Tel. +62 21 8230025, Fax +62 21 8230026
Web: idn.sika.com
Email: sikacare@id.sika.com



SikaTop-121-en-ID-(03-2018)-1-1.pdf

Product Data Sheet
SikaTop®-121
March 2018, Version 01.01
020302040050000001